

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 4 of 24

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A method for producing pulp and lignin from lignocellulosic material, the pulp comprising cellulose, the method comprising:
 - (a) contacting the lignocellulosic material with an aqueous nitric acid solution to impregnate the lignocellulosic material, the aqueous nitric acid solution comprising from about 10% to about 40% by weight of the nitric acid;
 - (b) heating the lignocellulosic material in two stages, the first heating stage being carried out ~~for a period of time which is sufficient at a temperature below 75 °C for at least 15 minutes~~ to depolymerize lignin within the lignocellulosic material without substantially degrading the cellulose or lignin in the lignocellulosic material, the second heating stage being carried out at or above the boiling point of the nitric acid to distill off the nitric acid;
 - (c) contacting the lignocellulosic material with an aqueous alkaline solution under heat to solubilize lignin in the alkaline solution, leaving a black liquor;
 - (d) removing the pulp from the black liquor;
 - (e) adding sufficient acid to the black liquor to precipitate the lignin; and
 - (f) removing the lignin from the liquor.
2. (Canceled)

BEST AVAILABLE COPY

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 5 of 21

3. (Currently amended) A method according to claim 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) for at least 30 minutes.
4. (Currently amended) A method according to claim ~~[[3]]~~ 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) from about 12 hours to about 24 hours.
5. (Currently amended) A method according to claim 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) under heat.
6. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) at a temperature from about 50 °C to below the boiling point of the nitric acid.
7. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the aqueous nitric acid solution in step (a) comprises from about 10% to about 30% by weight of the nitric acid.
8. (Original) A method according to claim 7 wherein the aqueous nitric acid solution comprises from about 15% to about 30% by weight of the nitric acid.
9. (Currently amended) A method according to claim 8 wherein the aqueous nitric acid solution comprises from about 20% to about 25% by weight of the nitric acid.
10. (Currently amended) A method according to claim ~~[[2]]~~ 7 wherein the aqueous nitric acid solution comprises from about 10% to about 15% by weight of the nitric acid.
11. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the temperature during the second heating stage of step (b) is from about 73 °C to below 100 °C.
12. (Original) A method according to claim 11 wherein the temperature during the second heating stage of step (b) is from about 90 °C to about 95 °C.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 6 of 21

13. (Canceled)
14. (Currently amended) A method according to claim ~~[[13]]~~ 1 wherein the temperature during the first heating stage of step (b) is ~~[[from]]~~ at least about 50 °C ~~to about 75 °C~~.
15. (Original) A method according to claim 14 wherein the temperature during the first heating stage of step (b) is from about 60 °C to about 70 °C.
16. (Original) A method according to claim 14 wherein the temperature during the first heating stage of step (b) is from about 50 °C to about 60 °C.
17. (Currently amended) A method according to claim 14 wherein the temperature during the first heating stage of step (b) is ~~[[from]]~~ at least about 70 °C ~~to about 75 °C~~.
18. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the first heating stage in step (b) is carried out for ~~at least 15~~ more than 75 minutes.
19. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the aqueous alkaline solution comprises sodium hydroxide or potassium hydroxide or a combination of sodium hydroxide and potassium hydroxide.
20. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the aqueous alkaline solution comprises an amount of alkali solute which is at least the normal equivalent of the nitric acid in the aqueous nitric acid solution in step (a).
21. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the aqueous alkaline solution comprises an amount of alkali solute which is at least the molar equivalent of the nitric acid in the aqueous nitric acid solution in step (a).
22. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the acid added in step (e) is sulfuric acid.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 7 of 21

23. (Currently amended) A method according to claim [[2]] 1 wherein the amount of acid added in step (e) is at least the molar amount of the alkali in the aqueous alkaline solution in step (c).
24. (Original) A method according to claim 1 wherein the black liquor is cooled from the temperature in step (c) before the acid is added in step (e).
25. (Currently amended) A method according to claim [[2]] 1 wherein the temperature of the black liquor when the acid is added in step (e) is up to about 75 °C.
26. (Original) A method according to claim 25 wherein the temperature of the black liquor when the acid is added in step (e) is from about 5 °C to about 75 °C.
27. (Original) A method according to claim 26 wherein the temperature of the black liquor when the acid is added in step (e) is from about 5 °C to about 50 °C.
28. (Original) A method according to claim 27 wherein the temperature of the black liquor when the acid is added in step (e) is from about 25 °C to about 50 °C.
29. (Original) A method according to claim 25 wherein the temperature of the black liquor when the acid is added in step (e) is from about 50 °C to about 75 °C.
30. (Currently amended) A method according to claim 1 wherein any aqueous nitric acid solution not absorbed by the lignocellulosic material in step (a) is removed prior to heating the lignocellulosic material in step (b).
31. (Currently amended) A method according to claim 30 comprising collecting any aqueous nitric acid solution which is removed prior to step (b) and recycling the collected aqueous nitric acid solution for use in step (a), and comprising collecting any nitric acid which is distilled off in step (b) and recycling the collected nitric acid for use in step (a).

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 8 of 21

32. (Original) A method according to claim 1 comprising contacting the lignocellulosic material with water before step (a) to increase the moisture content in the lignocellulosic material.
33. (Original) A method according to claim 1 wherein the starting moisture content of the lignocellulosic material is from about 30% to about 55% by weight of water.
34. (Original) A method according to claim 1 wherein the starting lignocellulosic material comprises undigested lignocellulosic material previously subjected to the method.
35. (Currently amended) A method according to claim 1 wherein the starting lignocellulosic material comprises wood chips, wood shavings[[,]] or sawdust or a combination of two or more of wood chips, wood shavings and sawdust.
36. (Currently amended) A method according to claim 1 wherein the starting lignocellulosic material comprises pieces of rye, wheat[[,]] or hemp or a combination of two or more of rye, wheat and hemp.
37. (Original) A method according to claim 1 wherein an amber liquor is left following the removal of the lignin, and comprising processing the amber liquor after the lignin has been removed.
38. (Original) A method according to claim 37 wherein the amber liquor is processed to produce unicellular proteins or alcohols or both.
39. (Original) A method according to claim 1 wherein any water which is produced as a reaction byproduct in one or more of the steps is collected and recycled for use in the method.
40. (Currently amended) A method according to claim [[2]] 1 wherein steps (a) and (c) and the first heating stage in step (b) are each carried out at a temperature from about 50 °C to [[about]] below 75 °C.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 9 of 11

41. (Original) A method according to claim 1 wherein at least one of the heating of the impregnated lignocellulosic material in step (b), the contacting the lignocellulosic material with the aqueous alkaline solution in step (c) and the adding the acid in step (e) is carried out with agitation.
42. (Original) A method according to claim 1 wherein the heating of the impregnated lignocellulosic material in step (b), the contacting the lignocellulosic material with the aqueous alkaline solution in step (c) and the addition of the acid in step (e) are each carried out with agitation.
43. (Original) A method according to claim 1 wherein the method is carried out at atmospheric pressure.
44. (Original) A method according to claim 1 comprising washing, pressing, bleaching and drying the pulp removed in step (d).
45. (Original) A method according to claim 1 comprising drying the lignin removed in step (f).
46. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein step (c) is carried out at a temperature up to about 75 °C.
47. (Original) A method according to claim 46 wherein step (c) is carried out at a temperature from about 5 °C to about 75 °C.
48. (Original) A method according to claim 47 wherein step (c) is carried out at a temperature from about 50 °C to about 75 °C.
49. (Original) A method according to claim 46 wherein step (c) is carried out at a temperature from about 20 °C to about 50 °C.
50. (Original) A method according to claim 47 wherein step (c) is carried out at a temperature from about 30 °C to about 40 °C.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 10 of 21

51. (Original) A method according to claim 47 wherein step (c) is carried out at a temperature from about 40 °C to about 50 °C.
52. (Currently amended) A method according to claim 1 wherein the lignocellulosic material is immersed in the aqueous nitric acid solution in step (a).
53. (Currently amended) A method according to claim 1 wherein the lignocellulosic material is sprayed with the aqueous nitric acid solution in step (a).
54. (Currently amended) A method for producing pulp and lignin from lignocellulosic material, the pulp comprising cellulose, the starting moisture content of the lignocellulosic material being from about 30% to about 55% by weight of water, the method comprising:
- (a) contacting the lignocellulosic material for at least 12 hours with an aqueous nitric acid solution to impregnate the lignocellulosic material, the aqueous nitric acid solution consisting only of nitric acid and water and comprising from about [[10%]] 24.15% to about 40% by weight of the nitric acid,
 - (b) heating the impregnated lignocellulosic material in two stages, the first heating stage being carried out at a temperature from about 50 °C to about below 75 °C for a period of time which is sufficient at least 15 minutes to depolymerize lignin within the lignocellulosic material without substantially degrading the cellulose or lignin in the lignocellulosic material, the second heating stage being carried out at or above the boiling point of the nitric acid to distill off the nitric acid;
 - (c) contacting the lignocellulosic material with an aqueous alkaline solution at a temperature from about 50 °C to about 75 °C to solubilize lignin in the alkaline solution, leaving a black liquor, the aqueous alkaline solution comprising an amount of alkali which is at least the normal amount of the nitric acid in the aqueous acid solution in step (a);

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 11 of 21

- (d) removing the pulp from the black liquor;
- (e) cooling the black liquor and then adding an acid to the black liquor to acidify the solution to precipitate the lignin;
- (f) removing the lignin, leaving an amber liquor; and
- (g) processing the amber liquor to produce unicellular proteins or alcohols or both,

wherein any aqueous nitric acid not absorbed by the lignocellulosic material in step (a) is removed and collected following step (a) prior to heating the lignocellulosic material in step (b) and then recycled for use in step (a), and wherein any nitric acid which is distilled off is collected prior to contacting the lignocellulosic material with the alkaline solution in step (c) and then recycled for use in step (a), and wherein the heating of the lignocellulosic material in step (b), the contacting the lignocellulosic material with the aqueous alkaline solution in step (c) and the addition of the acid in step (e) are each carried out with agitation.

55. (Currently amended) A method for producing pulp and lignin comprising the steps of contacting lignocellulosic material with an aqueous nitric acid solution which is free of ammonium ions and aluminum and which comprises from about 10% to about 40% by weight of nitric acid and, after removing any nitric acid not absorbed by the lignocellulosic material, heating the lignocellulosic material at a temperature up to about 75 °C for at least 15 minutes to effect the acid-catalyzed hydrolytic depolymerization of the lignin in the lignocellulosic material without substantially degrading the cellulose or lignin in the lignocellulosic material, the nitric acid solution-contacting and heating steps being carried out before the lignocellulosic material is digested in an alkaline liquor, the pulp being removed following the digestion of the lignocellulosic material in the alkaline liquor, the lignin being removed after being precipitated out with the addition of an acid to the black liquor produced following the digestion of the lignocellulosic material in the alkaline liquor, wherein the pulp comprises cellulose.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 12 of 21

56. (Canceled)
57. (Currently amended) A method according to claim [[56]] 55 comprising heating the lignocellulosic material after depolymerizing the lignin but before digesting the lignocellulosic material, at a temperature above the boiling point of the nitric acid in order to distill off the nitric acid.
58. (Original) A method according to claim 44 wherein any liquor that is removed from the pulp by pressing is collected and added to the black liquor prior to adding the acid in step (e).
59. (Original) A method according to claim 45 wherein any liquor which is removed from the lignin during drying is collected and added to the liquor after step (f), and wherein the liquor is processed after the lignin has been precipitated and removed.
60. (Currently amended) [[The]] A method [[of]] according to claim 1 wherein enough acid is added to the solution in step (e) to lower the pH of the solution to an acidic pH.
61. (Currently amended) A method for treating lignocellulosic material, the starting moisture content of the lignocellulosic material being from about 30% to about 55% by weight of water, the method comprising:
- (a) contacting the lignocellulosic material with an aqueous nitric acid solution to impregnate the lignocellulosic material, the aqueous nitric acid solution being free of ammonium ions and aluminum and comprising from about [[10%]] 24.15% to about 40% by weight of the nitric acid;
 - (b) heating the lignocellulosic material in two stages, the first heating stage being carried out at a temperature below 75 °C for at least 15 minutes for a period of time which is sufficient to depolymerize lignin within the lignocellulosic material without substantially degrading the cellulose or

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 13 of 21

lignin in the lignocellulosic material, the second heating stage being carried out for about 11 to 59 minutes at or above the boiling point of the nitric acid to distill off the nitric acid, wherein any aqueous nitric acid solution not absorbed by the lignocellulosic material in step (a) is removed prior to heating the lignocellulosic material in step (b);

- (c) contacting the lignocellulosic material with an aqueous alkaline solution under heat at a temperature up to about 75 °C to solubilize lignin in the alkaline solution, leaving a black liquor; and
 - (d) removing the pulp from the black liquor, the pulp comprising cellulose.
62. (Currently amended) A method according to claim ~~[[2]]~~ 1 wherein the amount of acid added in step (e) is at least the normal amount of the alkali in the aqueous alkaline solution in step (c).
63. (Canceled)
64. (New) A method according to claim 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) for more than 200 minutes.
65. (New) A method according to claim 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) for at least 6 hours.
66. (New) A method according to claim 1 wherein the lignocellulosic material is contacted with the aqueous nitric acid solution in step (a) for at least 12 hours.
67. (New) A method according to claim 1 wherein the aqueous nitric acid solution comprises more than 22% by weight of the nitric acid.
68. (New) A method according to claim 1 wherein the aqueous nitric acid solution comprises at least about 24.15% by weight of the nitric acid.

Application No. 10/728976
Amendment dated 8 March 2005
Reply to Office Action of 8 December 2004

Page 14 of 21

69. (New) A method according to claim 14 wherein the temperature during the first heating stage of step (b) is at least 60 °C.
70. (New) A method according to claim 1 wherein the second heating stage in step (b) is carried out for at least 11 minutes.
71. (New) A method according to claim 1 wherein the second heating stage in step (b) is carried out for about 11 to 59 minutes.
72. (New) A method according to claim 1 wherein the aqueous nitric acid solution in step (a) is free of ammonium ions and aluminum.
73. (New) A method according to claim 1 wherein the aqueous nitric acid solution in step (a) consists only of nitric acid and water.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.